



PRODUCT HIGHLIGHTS

5374 Machine Polish

DESCRIPTION:

Ultimate Finish System™ Machine Polish's advanced technology eliminates 2000 grit or finer imperfections and scratches leaving a high gloss finish. Machine Polish is safe on all paints and is easy to clean. Its increased open time allows you to buff longer using less material for an impeccable shine. For best results, use with Transtar's White Foam Pad.

PRODUCTS:

5374 Machine Polish, Quart (0.946 L), 6/case





SURFACE PREP:

Wipe surface clean with clear, dry cloth



SANDING:

1200-2000 grit, wet or dry Finish sand wih 1500 - 2000 grit.



POLISHING:

1000 RPM White Foam Pad (#5282)



NEXT STEP:

Refer to TDS 406 for next step.

See next page for more detailed product application. See website for this document in other languages.

Vea la página siguiente para un uso más detallado del producto. Vea el Web site para este documento en español.

Voir la prochaine page pour une application plus détaillée de produit. Voir le site Web pour ce document en français.





PRODUCT DATA

5374 Machine Polish

DESCRIPTION:

Ultimate Finish System™ Machine Polish's advanced technology eliminates 2000 grit or finer imperfections and scratches leaving a high gloss finish. Machine Polish is safe on all paints and is easy to clean. Its increased open time allows you to buff longer using less material for an impeccable shine. For best results, use with Transtar's White Foam Pad.

PACKAGE SIZES:

5374 Machine Polish, Quart (0.946 L). 6/case

SURFACE PREPARATION:

Wipe surface clean with a clean dry cloth.

State Compliant

APPLICATION:

Shake container well before use. Note: Do not apply in direct sunlight or to a hot surface. Apply a 1.25" wide by 6" long ribbon (for every 2' x 2' area to polish) of Machine Polish and spread with pad to minimize sling. Using a buffer at low speed (1000 rpm), work material in a circular overlapping motion with White Foam Machine Polish Pad #5282. Make sure to apply sufficient pressure to remove imperfections and scratches. Continue buffing until desired gloss is obtained. Care must be taken to avoid scouring the finish. Finish by removing any polish residue with clean microfiber cloth.

SANDING:

Sand with 1200 grit wet or dry until imperfections or defects are removed. Finish sand with 1500 - 2000 grit.

TECHNICAL DATA:

APPEARANCE: White V.O.C. CONTENT: (RTU) 9.4%

SHELF LIFE: 1 year (Unopened)

ADVANTAGES:

- Fast cut
- Good work time
- Great gloss
- · Easy clean up

COMPETITION:

3M 06064 Machine Polish Presta 1335 Chroma Ultra Polish Evercoat 100038 Meguiar's 205

Wizards Finish Cut

DISCLAIMER: The technical information and suggestions for use have been compiled for your guidance and usage. Such information is based on Transtar Autobody Technologies experience and research and is believed to be reliable. As Transtar has no control over conditions in which the product is used, stored, or otherwise handled, the above information does not constitute a warranty. Buyers must assume responsibility for the suitability of the product for their purposes.

See website (www-tat-co.com) for this document in other languages.

Vea el Web site (www.tat-co.com) para este documento en español.

Voir le site Web (www.tat-co.com) pour ce document en français.

TRANSTAR AUTOBODY TECHNOLOGIES • 2040 HEISERMAN DRIVE, BRIGHTON, MI 48114 • (800) 824-2843 FAX (800) 477-7923 • EMAIL: info@tat-co.com