

# PlastiKote®

THE PERFECT FINISH™

## PlastiKote® Engine Enamel



### Product Description

PlastiKote® Engine Enamel has been the restorers' choice for over 75 years. It is easy to use and dries to an extremely rugged, high heat-resistant finish. Repeated exposure to engine heat up to 500° F will fuse engine enamel to the surface to increase bonding strength. It is the answer for engine restorations and similar applications where a tough, high-heat finish is required.

### Features

- Resists temperatures up to 500 °F
- Fully resistant to gasoline and oil
- Will not weaken, crack, lift or peel
- OEM color matched to exact standards

### Colors Information

	Part Number
Hot Rod Yellow	198
Hot Rod Green	199
Chev Orange	200
Chev Blue	201
Universal Gray	202
Universal Black	203
Old Frd Blue	205
Frd Red	206
Aluminum	207
Ponti Blue	208
Universal Red	209
Hot Rod White	211
Low Gloss Black	215
New Frd Gray	216
GM Corp. Blue	221
Universal Gold	223
Frd Blue	224
Alpine Green	225
Chrys Orange	226
Ponti Blue Metallic	227
Gray Engine Primer	228
Clear	229
Flat Black	230
Chrys Blue	232
Cummins Beige	233

### Typical Properties (198 Hot Rod Yellow)

#### Dry Time:

**To the touch:** 1 hour

**Recoat:** Within 4 hours or after 36 hours

#### Surface Coverage:

Coverage varies depending on surface color and porosity.

### Recommended Uses

- Engines
- Other applications where a tough, high-heat finish is required

### Can Size and Fill Weight

**Can Size:** Paint or Paint Related Material. Protect from freezing.

**Fill Weight:** 12 oz.

## Surface Preparation and Application

Read the Lead Warning in Cautions section. **USE ONLY WITH ADEQUATE VENTILATION.**

Apply to clean, dry surface when temperature is between 60–80 °F and humidity is below 60%. Prime bare metal with #228 Gray Primer. Shake can until agitator ball rattles freely for two minutes. Shake can during use. Hold can 8-10 inches from surface and spray with short dusting strokes. Apply 2-3 light mist coats. Allow paint to dry 10 minutes between coats. Apply #229 Clear for additional gloss and durability. Recoat within 4 hours or after 36 hours, otherwise paint may wrinkle or lift. Dry to touch in one hour. To prevent can from clogging after use, turn can upside down and spray for 3 seconds.

## Cautions (198 Hot Rod Yellow)

**CONTAINS NO CFC's – In accordance with Federal regulations which prohibit the use of CFC propellants in aerosols.**

**WARNING: CONTAINS ACETONE, XYLENE, ETHYLBENZENE, PETROLEUM DISTILLATES, ALUMINUM, PSEUDO CUMENE.** Vapor harmful. May affect the brain or nervous system causing dizziness, headache or nausea. Causes eye, skin, nose and throat irritation. Do not puncture or incinerate (burn) container. Exposure to heat or prolonged exposure to sun may cause bursting. Do not expose to heat or store at temperatures above 120 °F (49 °C). Replace cap after each use. **Vapors may ignite explosively.** Keep away from heat, sparks and flame. Do not smoke. Extinguish all flames and pilot lights and turn off stoves, heaters, electric motors and other sources of ignition during use and until all vapors are gone. Prevent build-up of vapors by opening all windows and doors to achieve cross ventilation. **Use only with adequate ventilation.** Do not breathe dust, vapors or spray mist. Ensure fresh air entry during application and drying. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headache or dizziness, wear an appropriate, properly fitted respirator (NIOSH approved) during and after application. Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes, skin and clothing.

**WARNING:** This product contains a chemical known to the State of California to cause cancer.

**Delayed effect from long-term exposure: NOTICE –** Reports have associated repeated or prolonged occupational overexposure to solvents with permanent brain or nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful or fatal.

**FIRST AID:** If you experience difficulty in breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately. In case of eye contact, flush immediately with plenty of water for at least 15 minutes and get medical attention; for skin, wash thoroughly with soap and water. If swallowed, do not induce vomiting. Get medical attention immediately.

**DO NOT TAKE INTERNALLY.**

**KEEP OUT OF REACH OF CHILDREN.**

**For additional safety and chronic health hazard information, refer to the Material Safety Data Sheet for this product.**

**EMERGENCY MEDICAL TELEPHONE:  
1-888-345-5732**

**WARNING!** If you scrape, sand or remove old paint, you may release lead dust. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a NIOSH-approved respirator to control lead exposure. Clean-up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

The data on this sheet represents typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Valspar assumes no obligation or liability for use of this information. **UNLESS VALSPAR AGREES OTHERWISE IN WRITING, VALSPAR MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. VALSPAR WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product, is the replacement of the defective product, or a refund of its purchase price, at our option.

**PlastiKote®**  
THE PERFECT FINISH™

1191 Wheeling Rd, Wheeling, IL 60090 866-222-8714  
[www.plastikote.com](http://www.plastikote.com)

12/10

PDS 198