519

MEDIUM GRADE PAPER MASKING TAPE

INTERTAPE POLYMER GROUP

TECHNICAL DATA SHEET

DESCRIPTION

A beige, conformable, semi-bleached crepe paper masking tape coated with pressure-sensitive natural rubber adhesive. Capable of withstanding bake temperatures up to 180°F (82°C) for up to one hour and/or exposure to ultra-violet (UV) light for up to five hours. Offers consistent conformability and tensile strength for general purpose bundling, protecting, and various industrial applications.

PRODUCT APPLICATION

Interior paint masking, spray painting (air-dry) autos, boats, etc., boat manufacturing (fiberglass), silk screening, mail rooms, marble manufacturing (man-made), golf club shaft (build-up), carpet pad / pad splicing, freezer tape, and light bundling, packaging, splicing and tabbing.

GOVERNMENT COMPLIANCE

Product can be qualified to meet Federal Specifications PPP-T-42C, Type I and UU-T-106, Type I and C.I.D. A-A-883, Type I.

intertape polymer group™

3647 Cortez Road West | Bradenton, FL 34210 | USA Customer Service: 800.IPG.8273 | 800.474.8273

Tape Technical Service: 877.447.4832 www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

NOMINAL VALUES

Color

The following data are nominal values based on PSTC, ASTM and other standard test. The data should not be considered as specifications.

Backing	Crepe Paper
Adhesive	Natural/Synthetic Rubber
Adhesion to Steel (oz/in of width) PSTC-1	36 (9.8 N/25mm)
Tensile Strength (lbs/in of width) PSTC-31	23 (100 N/25mm)
Elongation (at break) PSTC-31	7%
Total Thickness (mils) PSTC-33	6.0 (0.152mm)
Quick Stick to Steel (oz/in of width) PSTC-5	17 (4.6 N/25mm)

Beige



EFFECTIVE: 02/10