

PRODUCT FEATURES & APPLICATION



Dry 2 hours +-
Also wet on wet
Paintable 30 minutes**



PAGE 1 of 2

Dominion Sure Seal Ltd.

6175 Danville Road, Mississauga, Ontario, Canada L5T 2H7

EUROPEAN TEXTURIZER

TEL (905) 670-5411

FAX (905) 670-5174

Stock Number BSTE, Colour: Grey
Part Number 9123 (1 Liter) (33.8oz)
Size: 1 Liter (33.8oz)
European Style Can

Description:

European Texturizer Gravel Guard is a paintable **VERY HIGH** solid texturizer agent. With the use of our European Shutz gun and its variable spray valve all OEM and after market textures can be duplicated on metal, wood, plastic and vinyl roofs.

May be painted wet on wet after 30 minutes

Features:

- Can be painted after 30 minutes
- A very high build coating.
- Every texture can be duplicated

Surface Preparation:

1. Surfaces must be clean and dry.
2. Clean surface with a some fast drying solvent. We strongly recommend Sure Solv Part # BSS (10058) and allow to dry.
3. For applying on aluminum our Super Acid Etch product SEPA (24010) is highly recommended.
4. Texturizer is high build and ready for use however if you want to have very light texture, you may wish to reduce it with up to 5% of lacquer thinners..
5. Lacquer or Cellulose thinners may also be used to clean the BUPE gun.

Application Instructions:

1. Shake the can well.
2. Attach the BUPAE gun to the Euro Texturizer can.
3. Allow 10-15 minutes between coats to let the solvent flash off.
4. One coat will give you between 100-150 microns at a pressure of 43-72 PSI. Spray distance should be 30cm or 12 inches.
5. More or less pressure will give a flatter textured look. Also the BUPE gun has the advantage of being able to vary the texture by adjusting the pressure nozzle feature on the gun.
6. Dry time is about 2 hours at 70f or 30 minutes in the bake oven at low bake (60c). Euro Texturizer can also be painted wet on wet after a 30 minute dry time with 2K paints.
7. The use of a U.V. clear coat on metal and plastic is recommended for high gloss and protection from fading.

Note: Avoid applying any materials on or near catalytic converters, mufflers due to extreme heat.

In the event the MSDS (Material Safety Data Sheet) on this product is not in your files, you can request one from Dominion Sure Seal Regulatory Compliance at 1800 265-0790, ext. MSDS.

BSTE May 2004



Dry time 2 hours +or- Paintable in 30 minutes**

Size: 1 Liter European

EUROPEAN Texturizer GRAVEL GUARD

Continued

TECHNICAL SPECIFICATIONS

Consistence;	Liquid with good sag resistance
Colour:	GRAY
Viscosity (20c, 72f):	Brookfield (after 2 min mixing) 12-160 Pas (spindle 5/V1/2)
Density (20c, 72f):	DIN51757 1.33-1.387 Kg.ltr
Solid Content:	Sartorius 60%-68%

PROPERTIES

Dry to touch;	At+20C 65%RH 15-30 mins (+600mu)
Completely dry:	At+20C 65%RH 60-90 hours (+600mu)
	At 60C (<u>oven</u>)_20-30 minutes (+600mu)
	At 60C (Infra Red) 20-30 minutes (+600mu)

Paintable @+ 20C 65%RH:

2K Acrylic System	After 30 minutes (wet on wet)
Basecoat system	After 30 minutes (wet on wet)
Waterbase system	Possible after FULL drying
Brookfield (after 2 min mixing)	140-180 Pas (Spindle 5/V1/2)

Colour:	
Viscosity (20c, 72f):	
Chemical resistance:	Hardened against water, saltspray, oil, soft acids and bases
Temperature resistance:	Hardened against -25C - +80C
Usage:	With +- mu wet layer +0.8kg/m2 +-0.6 ltr/m2
Non reversible:	With solvents
Cleaning:	Fresh material solvents by hand

Visit our web site at www.dominionsureseal.com or phone 1-800 265 0790 for more information

Call 1-800-265-0790 or visit us on the web www.dominionsureseal.com