



PRODUCT DATA

4361-F, 4363-F, 4364-F Quick Dry Rubberized Undercoat

DESCRIPTION:

Quick Dry Rubberized Undercoat is a rapid-drying highly protective automotive coating for autobody interiors and underhood applications. Resists rust and abrasion as it seals out dust and moisture. Deadens sound. Excellent adhesion to painted and unpainted surfaces. This product is 50 state compliant and meets all regulations for sale in the USA and Canada. Exceeds 500 hours of salt spray using ASTM B117 method.

APPLICATION:

Aerosol: Shake well. Wash and solvent clean surface to remove all rust, dirt and grease using Aqua SCAT #6354/6354, Speedi SCAT #6321 or SCAT #6311. For best results, use at room temperature. Hold can in an upright position and spray 8-10 inches from surface, using steady light strokes. Several light coats will produce a better finish than one heavy coat. Remove overspray with Acry Solvent #9783/9784. May be topcoated after one hour.

Quart/Gallon: Stir thoroughly before use. Wash and solvent clean surface to remove all rust, dirt and grease. Apply with a gun, using air pressure of 40 PSI at the gun. Allow to dry at least 4 hours before painting. Thoroughly clean gun with Acry Solvent #9783/9784 immediately after use. May be topcoated after an hour.

NOTE: This product contains asphalt which may stain light colored topcoats.

SALES POINTS:

- Fast drying, easy to apply.
- Excellent abrasion resistance.
- Retains black color.
- Won't sag or run.
- Dries completely, yet remains flexible.
- Seals out dust, fumes, heat and cold.
- Aerosol package requires no clean-up
- 50 State & Canadian Compliant

COMPETITION:

3M Body Schutz
FE Rubberized Undercoating
Rusfree Rubberized Undercoating

(Refer to Material Safety Data Sheet for proper handling of products listed in this bulletin).

PACKAGE SIZE:

4361-F Quick Dry Rubberized Undercoat, Gallon (3.78 L), 2/case
4363-F Quick Dry Rubberized Undercoat, 24 oz. aerosol (710 ml), 6/case
4364-F Quick Dry Rubberized Undercoat, Quart (0.946 L), 6/case

DISCLAIMER: The technical information and suggestions for use have been compiled for your guidance and usage. Such information is based on Transtar Autobody Technologies experience and research and is believed to be reliable. As Transtar has no control over conditions in which the product is used, stored, or otherwise handled, the above information does not constitute a warranty. Buyers must assume responsibility for the suitability of the product for their purposes.

